

Test Method

Sampling of Loose Asphalt

RC 200.01

As for AS 2891.1.1, except that the sample size from Clause 6 of AS 2891.1.1 shall be as given in Table 1 of this document:

Table 1 Sample Sizes

Type of material to be sampled	Property to be determined	Minimum sample size*
Freshly mixed or supplied material	Bitumen or tar content and aggregate grading	4 kg
	Moisture content	1 kg
	Bulk density, stability and flow of laboratory compacted specimens	5 kg
	Maximum density	2 kg
Placed and compacted material (core specimens)	Bulk density	An isolated layer of the core
	Maximum density	1 kg (1 or more cores)

* Where referee samples are required the minimum sample size should be adjusted accordingly

Test Method - Revision Summary

RC 200.01 Sampling of Loose Asphalt

Date	Clause Number	Description of Revision	Authorised by
June 2013	Full document	Re-issued without change	Manager – Construction Materials